

NORTHWEST LABORATORIES *of Seattle, Incorporated*

ESTABLISHED 1896

Technical Services for: Industry, commerce, Legal Profession & Insurance Industry

241 South Holden Street • Seattle, WA 98108-4359 • Phone: (206) 763-6252 • Fax: (206) 763-3949 www.nwlabsl896.com

December 9, 2010

Quick & Easy Concrete, Inc.
P.O. Box 1546
Woodinville, WA 98072

Attn: Cliff Wilson

Re: Chloride Ion Content
AASHTO T260
N.W. Labs Report #**E84621**

Dear Mr. Wilson:

Per your request, the submitted concrete core was tested for chloride ion content per AASHTO T260. The core was aged for 28 days prior to testing.

The following results were obtained.

Analysis: Per ASSHTO T260

<u>Sample ID</u>	<u>Results (%)</u> <u>by weight of concrete</u>	<u>Result (%)</u> <u>by weight of cement</u>	<u>Specified</u>
11-9-10 core	0.005	0.042	0.10% max

Note: The water content was assumed to be 47% of weight of cement.

Sincerely,

NORTHWEST LABORATORIES, INC.



Omar Simon, Chemist

nbe

www.nwlabsl896.com
osimon@nwlabsl896.com